

# DADCO

## Oxidized Bitumen 115/15



### Description

Oxidized Bituménous compound used in bonding layers of felt and damp proofing above under-ground foundations. Recommended for use in extremely hot region.

### Application

To be applied by Brush or Rollers.

### Packages

14 kgs, 110 kgs, 125 kgs, 180 kgs.

### Technical Data

| PROPERTIES                                 | MIN | MAX | STANDARD  |
|--|-----|-----|-----------|
| PENETRATION AT 25°C<br>100 GM 5 Secs (dmm) | 10  | 20  | ASTM D-5  |
| SOFTENING POINT (°C)                       | 110 | 120 | ASTM D-36 |
| Flash Point (°C)                           | 260 | --  | ASTM D-92 |
| LOSS ON HEATING WEIGHT (%)                 | --  | 0-3 | ASTM D-6  |

SPECIFICATIONS CONFIRM WITH ONORM B - 3611.